

THERMAL INSULATION AND AIR BARRIER
 ESR-699 CCRR-0371 | CSI Section: 07 21 00

PRODUCT DESCRIPTION

Accufoam OC is a two-component, one-by-one-by-volume spray-applied polyurethane foam. Accufoam OC is a high-yield, low-density, no-mix, spray-applied insulation foam, which contains zero ozone-depleting blowing agents and is designed to provide good thermal performance and a significant control of air infiltration of an air-barrier assembly. Accufoam OC is 100% water blown.



PRODUCT DATA

PROPERTY	TEST METHOD	VALUE
R-VALUE @ 1"	ASTM C 518	3.7
R-VALUE @ 3.5"	ASTM C 518	13
CORE DENSITY pcf	ASTM D 1622	0.45
OPEN-CELL CONTENT %	ASTM D 6226	>90
DIMENSIONAL STABILITY %	ASTM D 2126	<9.3
TENSILE STRENGTH psi	ASTM D 1623	4.2
AIR PERMEANCE	ASTM E 2178	<0.02
SOUND TRANSMISSION CLASS	ASTM E 90	38
NOISE REDUCTION COEFFICIENT	ASTM C 423	0.55
SURFACE BURNING CHARACTERISTICS	ASTM E 84	Class-1
RE-ENTRY PERIOD W/10 ACH	ASTM D8445-22A	1 Hour
RE-OCCUPANCY PERIOD W/10 ACH	ASTM D8445-22A	1 Hour
VISCOSITY-ISO AT 77F (CPS)		200
VISCOSITY-RESIN AT 77F (CPS)		320

BURN CHARACTERISTICS

PROPERTY	TEST METHOD	VALUE
FLAME SPREAD INDEX	ASTM E 84	≤ 25
SMOKE DEVELOPMENT	ASTM E 84	≤ 450

IGNITION BARRIER AC377X

TYPE	WFT	WALL	CEILING
DC315	4 MIL MIN	8 INCH MAX	14 INCH MAX
FS-IB	6 MIL MIN	10 INCH MAX	15 INCH MAX
No Burn Plus XD / Plus ThB	6 MIL MIN	8 INCH MAX	14 INCH MAX

THERMAL BARRIER NFPA286

TYPE	WFT	WALL	CEILING
DC315	18 MIL MIN	10 INCH MAX	12 INCH MAX

UNVENTED ATTIC ASSEMBLIES CCRR 0354

LOCATION	MAX THICKNESS (IN.)	MIN THICKNESS (IN.)
ROOF DECK	18"	3"
ATTIC WALL	18"	3"

*Consult with Creative Polymer Solutions Technical Department for Unvented Attic Guide drawings and specifications.

APPLICATION PARAMETERS

STORAGE TEMPERATURE	60° – 90°
AMBIENT TEMPERATURE	40° – 120°
SUBSTRATE TEMPERATURE	40° – 120°
MOISTURE CONTENT OF SUBSTRATE	Less than 19%
MAXIMUM LIFT PER PASS	Not to exceed 8"

EQUIPMENT SETTINGS

PRE-HEATER: (A) COMPONENT – ISO	120° – 140°
PRE-HEATER: (B) COMPONENT – RESIN	120° – 140°
HOSE HEAT	120° – 140°
FLUID PRESSURE – DYNAMIC	1100 – 1400 psi
MIXING RATIO	1:1 by Volume
RECOMMENDED MIX CHAMBER SIZE	10-15 lbs./minute (i.e. 01-Graco AR4242)
STORAGE STABILITY (SHELF LIFE)	6 Months

*The values represented in the Equipment Settings chart provides initial optimum settings. Actual operating ranges will vary as ambient air; humidity, moisture, and substrate temperatures vary. Extreme conditions will affect the yield, adhesion and cured physical properties of the foam. Applicator must make adjustments as conditions vary.

Disclaimer: The data herein is to assist customers who desire to use our products to determine if the products are safe and suitable for their applications. The data presented herein is not intended for use by non-professional applicators, or those persons who do not purchase or utilize this product in the normal course of their business. Customers further assume full responsibility for quality control, testing and determining whether the products are suitable for each individual application. To the best of Creative Polymers knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE SUED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF CREATIVE POLYMER'S TERMS AND CONDITIONS OF SALE.